

WALLTITE® CM01 Long Term Thermal Resistance Values Reference Guide

The Long Term Thermal Resistance (LTTR) data presented in this table has been derived from testing conducted according to the requirements of standards,

CAN/ULC-S705.1-15, Standard for Thermal Insulation – Spray Applied Rigid Polyurethane Foam, Medium Density – Material Specification and

CAN/ULC-S770-09, Standard Test Method for Determination of Long Term Thermal Resistance of Closed-Cell Thermal Insulating Foams.

Standard CAN/ULC-S77009 is referenced in standard CAN/ULC-S705.1-15 under subsection 2.1.

Furthermore, clause 5.5.8.2 of CAN/ULC-S705.1-15 stipulates the following:

“The thermal resistance value measured shall be the design thermal resistance value values.”

Standard CAN/ULC-S705.1-15 is referenced in the National Building Code of Canada under the following items:

Section 1.3 Referenced Documents and Organizations Sentence 1.3.1.2.(1) Applicable Editions (see Table 1.3.1.2.)

Section 5.10 Standards Sentence 5.10.1.1.(1) Compliance with Applicable Standards (see Table 5.10.1.1.)

Section 9.25 Heat Transfer, Air Leakage and Condensation Control Subsection 9.25.2 Thermal Insulation Article 9.25.2.2. Insulation Materials (CAN/ULC-705.1)

Standard CAN/ULC-S770-09 is referenced in the 2015 National Building Code of Canada in the explanatory note A-9.36.2.4.(1) (see Table A-9.36.2.4.(1)-D).

LTTR measurements were conducted by Exova Canada Inc. of Mississauga (ON), an independent laboratory, and are recorded in report no. 17-06-P0045B.

Additional information on the aging process of foam thermal insulations and the design thermal resistance of polyurethane foams is found in [Use of Field-Applied Polyurethane Foams in Buildings](#), Construction Technology Update No. 32, IRC-NRC, M.T. Bomberg, M.K. Kumaran (December 1999).

Thermal Resistance		Thickness	
R-Value (ft ² ·hr·°F/Btu)	RSI (m ² ·°C/W)	(inches)	(mm)
6	1.06	1.2	30
7	1.23	1.4	35
8	1.41	1.6	40
9	1.59	1.7	44
10	1.76	1.9	48
11	1.94	2.1	53
12	2.11	2.3	58
13	2.29	2.5	63
14	2.47	2.7	68
15	2.68	2.8	71
16	2.82	2.9	75
17	2.99	3.1	79
18	3.17	3.3	84
19	3.35	3.5	89
20	3.52	3.7	93
21	3.70	3.9	98
22	3.87	4.0	102
23	4.05	4.2	105
24	4.23	4.3	110
25	4.40	4.5	115
26	4.58	4.7	119
27	4.76	4.9	124
28	4.93	5.1	128
29	5.11	5.2	133
30	5.28	5.4	138
31	5.46	5.6	142
32	5.64	5.8	147
33	5.81	6.0	151
34	5.99	6.1	156
35	6.16	6.3	160
36	6.34	6.5	165
37	6.52	6.7	170
38	6.69	6.9	174
39	6.87	7.0	179
40	7.04	7.2	183
41	7.22	7.4	188
42	7.40	7.6	193
43	7.57	7.8	197
44	7.75	7.9	202
45	7.93	8.1	207

Data presented in this document is based on tests and information, which we believe to be reliable. This document is provided for information purposes only and without any representation, warranty or condition, expressed or implied, regarding its accuracy or completeness. Whether or not this data is used or relied upon is within the sole discretion and judgment of user. Since BASF Canada Inc. has no control over the conditions of handling, storage, use and disposal of the products, BASF Canada Inc., does not assume any responsibility or liability and expressly disclaims all liability for any claim, loss, damage, injury or expense resulting therefrom.